## LASER OPTICAL DENSITY CERTIFICATION

## D, AB3

Supplier: Thorlabs LimitedCert. Number: 51500Purchase Order Number: EO-265946Date: September 16, 2015Part Number: Dellner Rev D SampleRequirements: EN 12254: 2010(E), Paragraph 5.3 Resistance to Laser Radiation, Table 2.<br/>1400-10,600 nm Range.

## TEST PARAMETERS

Coating Type: n/a Test Wavelength: 10.6 µm Polarization: Linear Pulsewidth (Square): N/A Spot Diameter (1/e): 1.037 mm Test Prep: None Quantity: 3 Substrate Mat'l: Fabric Incidence Angle:  $0^{\circ}$ PRF : CW Transverse Mode: TEM<sub>00</sub> Axial Modes: Multiple Number of Sites: 1 Exposure Duration: 100 seconds

## TEST RESULTS:

<u>Sample</u>	<u>Measurement Level</u>
10	Sample maintains AB3 during irradiation.
10	Sample maintains AB3 during irradiation.
10	Sample maintains AB3 during irradiation.

COMMENTS: Laser penetrated fabric at AB4.

Spica Technologies certifies that this sample has been exposed to the parameters described above. All test and calibration data are maintained on file. All instrument calibration is traceable to NIST.

Test conducted by \_\_\_\_



18 Clinton Drive #3 Hollis, NH 03049 <u>www.spicatech.com</u> 603-882-8233